PLUVIAL CUBE HEAVY DUTY MODULE - DATA SHEET

| Pluvial Cube Module Dimensions* (mm) | Module Configuration | Units per m ³ | Module Volume (m³) | Storage Volume (m³) |
|--|-------------------------|--------------------------|-----------------------|------------------------|
| 500 (L) x 500 (W) x 550 (D) | Single | 7.27 | 0.1375 | 0.132 |
| 500 (L) x 500 (W) x 1075 (D) | Double | 3.72 | 0.2688 | 0.258 |
| 500 (L) x 500 (W) x 1600 (D) | Triple | 2.5 | 0.4 | 0.384 |

^{*} Bespoke modules with different configuration available







Double Module



Triple Module

| Product Data | Heavy Duty Pluvial Cube Module | |
|-------------------------------------|--------------------------------|--|
| Application | Stormwater Management | |
| Average Weight (kg) – single module | 8 | |
| Compressive Strength* (kN/m²) | 400 | |
| Lateral Strength* (kN/m²) | 200 | |
| Long Term Creep Testing** (kN/m²) | 200 | |
| Void Ratio (%) | 96 | |
| Surface Void Ratio (%) | Greater than 90 | |
| Minimum Backfill Cover# (mm) | 450 | |
| Maximum Backfill Cover (mm) | 5000 | |
| Material | Polypropylene | |
| Chemical resistance | Good | |
| Bacterial Resistance | Good | |
| UV Resistance | Good | |

Note: Other Modules with Compressive Strength more than 1500 kN/m² available

Note: All Alderburgh products are manufactured to the highest quality, being subjected to rigid quality control. However the company cannot control conditions of application and use of its products, thus any warranty, written or implied, is given in good faith for materials only. Alderburgh Ltd will not accept any responsibility for damage or injury arising from storage handling, misapplication or misuse of its products. All transactions are subject to our standard condition of sales, copies of which are available on request. Product design and specification are subject to change without further notice

Solutions House, Dane St. Rochdale, OL11 4EZ,

Tel: 01706 374416 Fax: 01706 376785 Email: sales@alderburgh.com



^{*} Modules tested using UKAS calibrated test machine, range 0 – 60 Tons, UDL, loading rate 0.2 kN/m²

^{**} Modules tested for long term creep testing for 90, 180 days and new ongoing test for 208 days.

 $^{^{\#}}$ Any cover less than 450 mm – contact ESS design department